

ABC FiberSpray

Asbestos Encapsulant/Sealant

Product Description

ABC FiberSpray is a convenient means for applying Fiberlock Technologies' time proven ABC Asbestos Binding Compound asbestos encapsulant. ABC FiberSpray dispenses encapsulant from a unique 8 ounce "airless-spray" can. This CFC-free "airless-spray" technology minimizes asbestos fiber release, and permits application of encapsulant in any position, even upside down (ideal for use inside glove bags). The ABC encapsulant inside each can was found to meet U.S. Environmental Protection Agency (EPA) test requirements performed at Battelle Laboratories Under Government Contract# 68-03-2552-T2005. Encapsulation of small, hard-to-access areas can be accomplished quickly and easily, without the need for bulky spray equipment.

6410-White

Application Information

APPLICATION INFORMATION

ENCAPSULATION: Use ABC FiberSpray to effectively encapsulate small areas of asbestos containing material (ACM).

GLOVEBAG USE: Place ABC FiberSpray in the pouch within the glovebag. Apply ABC FiberSpray to seal the friable pipe insulation ends after the insulation has been removed. Use ABC FiberSpray to "lockdown" residual microscopic fibers to the substrate.

BULK SAMPLE REPAIR: Apply ABC FiberSpray to friable areas after bulk samples have been removed from the ACM or suspected ACM.

PREPARATION

Shake well before spraying. If nozzle orifice is clogged, remove the dried film from the cap or replace with an extra nozzle (provided upon request).

APPLICATION

Apply ABC FiberSpray by spraying the surface from a distance of 8 to 12 inches.

CLEANUP

Clean the nozzle with warm soapy water before the coating dries.

PRECAUTIONS

Store in a dry place at temperatures between 40°F (4.5°C) and 90°F (32°C). Approved respirators must be used to prevent inhalation of asbestos fibers that may be present in the air. Protective clothing should be worn. Tools and drippings should be cleaned immediately with clean, soapy water before the coating dries. Careful consideration should be given to all Environmental Protection Agency (EPA), OSHA and state regulations in effect at

the time of application of ABC FiberSpray. The EPA, through the Office of Pesticides and Toxic Substances has issued reports headed "Guidance for Controlling Friable Asbestos-Containing Materials in Buildings," EPA 560/5 85-024, June 1985, and "Managing Asbestos in Place, A Building Owner's Guide to Operations and Maintenance Programs for Asbestos Containing Materials," 20T-2003, July 1990, containing the proper data, cautions, and procedures for asbestos control. Copies are available from the Environmental Assistance Division, TS-799, TSCA Assistance Information Service, U.S. EPA, 401 M Street SW, Washington, DC 20460, (202) 554-1404. Keep from freezing. Do not store at temperatures above 100°F. These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of this product are beyond our control. Neither Fiberlock Technologies, Inc., nor our agents shall be responsible for the use or results of use of this product or any procedures or apparatus mentioned. We recommend that the prospective user determine the suitability of ABC FiberSpray for each specific project and for the health and safety of personnel working in the area.

Properties

Product Specifications

Solids by Weight ± 2%:	51.4%
Solids by Volume ± 2%:	44.0%
Viscosity at 70°F:	60-75 Kreb units
Specular Gloss:	82° ± 5 @ 60°
Flash Point:	Non-combustible
Shelf Life:	36 Months Min. (Original Sealed Containers)
Calculated VOC:	64 grams/liter

ABC Fiberspray complies with the requirements for LEED® EQ Credit 4.2, low-emitting materials: paints and coatings.

Coverage

Individual Can:	35-40 ft ² /can
------------------------	----------------------------

Drying Times (@ 70 - 77°F , 50% R.H.)

To Touch:	1 hour
To Recoat:	4 hours
Minimum Application Temp.	50°F (10°C)

Available Package Sizes

8 Ounce Cans, 12 Cans Per Case	
Weight Per Gallon ± .5 lbs:	9.6 lbs/gal

Product Testing

Fire Rating:	ASTM E84 Class A
Flame Spread:	10
Fuel Contribution:	10
Smoke Density:	5
Test Facility:	Southwest Research Institute



*LEED® and related logo is a trademark owned by the U.S. Green Building Council and is used by permission.

ABC FiberSpray

Asbestos Encapsulant/Sealant

PRODUCT DATA SHEET

6410-White

Application Information

CAUTION!

KEEP OUT OF REACH OF CHILDREN.

Do not take internally. Close container after each use.

Keep from freezing.

Store between 40°F (4.5°C) and 90°F (32°C)

24 hour Emergency "CHEM-TEL" - 800.255.3924

For Technical Information call 800.342.3755

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of this product are beyond our control. Neither Fiberlock Technologies, Inc., nor its agents shall be responsible for the use or results of use of this product or any injury, loss or damage, direct or consequential. We recommend that the prospective user determine the suitability of this product for each specific project and for the health and safety of personnel working in the area.

ABC FiberSpray, the ABC FiberSpray Logo and other marks in this literature are trademarks of Fiberlock Technologies, Inc.

Fiberlock Technologies, Inc. • 150 Dascomb Rd • Andover, MA 01810 • www.fiberlock.com • 800.342.3755