

Fiberset PM

Post-Removal Surface Sealant

Product Description

7470-White, 7475-Clear, 7480-Blue

Fiberset PM is a pre-mixed "lockdown" sealing treatment for microscopic residual fibers present after the removal of Asbestos Containing Material (ACM). Available in white, blue or clear, Fiberset PM is a ready-to-use, Class A fire rated coating that provides a flexible barrier over residual fibers to ensure final air clearance. Fiberset PM is UL® classified for use as a primer for fireproofing replacement materials under the "Encapsulant Materials" section of the UL directory, and is compatible with leading brands of flooring adhesives. Fiberset PM is a water based coating that employs advanced 100% acrylic resin technology to extend the life expectancy of airless spray equipment.

Application Information

SURFACE PREPARATION

Warning! If you scrape, sand, or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

APPLICATION TOOLS

Apply Fiberset PM with airless spray equipment. Use the settings below when applying Fiberset PM:

- Spray Settings:
- Pressure: 1700-3000 P.S.I.
- Tips: .015-.021

PRODUCT APPLICATION

Stir Fiberset PM thoroughly to achieve a uniform consistency. Fiberset PM is pre-mixed; water-addition is not necessary. Minimum application temperature: 45°F.

LOCKDOWN: Sealing microscopic residual fibers after asbestos removal is mandatory on every project. Prior to post-removal air monitoring, apply one coat to all exposed surfaces. Fiberset PM has been accepted as part of a UL Classified Fireproofing System for use with Retro-Guard® manufactured by W.R. Grace & Co., Conn. Coverage should not be less than 500 sq. ft. per gallon on smooth surfaces.

PULL DOWN BY MISTING: Misting the contaminated air is an effective technique prior to post-removal air monitoring. To pull down free-floating asbestos fibers effectively, stand in the center of the

room and hold the spray gun as close to the ceiling as possible. A mist should be sprayed parallel to the ceiling in every direction or in a circle. Apply one coat to the polyethylene sheeting on the walls and floor prior to dismantling containment.

COVERAGE

Lockdown: Not less than 500 sq. ft. per gallon.

DRYING TIME @ 70°F 50% R.H

- To Touch: 1-2 hours
- To Recoat: 1-2 hours

CLEANUP

Tools and drippings should be cleaned with warm soapy water before coating dries. Follow equipment manufacturer's directions to clean spray equipment. Dispose of all waste according to current Local, State and Federal regulations.

PRECAUTIONS

Store in a dry place at temperatures between 40°F (4.5°C) and 90°F (32°C). Approved respirators must be used to prevent inhalation of asbestos fibers that may be present in the air. Protective clothing should be worn.

Careful consideration must be given to all EPA, OSHA, federal, state and local regulations in effect prior to the application of this product.

Properties

Product Specifications

Solids by Weight ± 2%:	11.0%
Solids by Volume ± 2%:	8.9%
Viscosity at 70°F:	50-60 Krebs units
Specular Gloss:	44° ± 3 @ 60°
Flash Point:	Non-combustible
Shelf Life:	36 Months Min. (Original Sealed Container)
Calculated VOC:	17-70 grams/liter

Fiberset PM complies with the requirements for LEED® EQ Credit 4.2, low-emitting materials: paints and coatings.

Coverage

Smooth Surfaces:	>500 ft ² /gal
Porous Surfaces:	350-500 ft ² /gal

Drying Times (@ 70 - 77°F , 50% R.H.)

To Touch:	1-2 hours
To Recoat:	1-2 hours
Minimum Application Temp:	50°F (10°C)

Available Package Sizes

5 gallon containers	
Weight Per Gallon ± .5lbs:	8.6 lbs/gal

Product Testing

UI Classification:	ASTM E-119
UL Category:	Encapsulant Materials



Fiberset PM

PRODUCT DATA SHEET

Post-Removal Surface Sealant

7470-White, 7475-Clear, 7480-Blue

Application Information

CAUTION!

KEEP OUT OF REACH OF CHILDREN.

Do not take internally. Close container after each use.

Keep from freezing

Store between 40°F (4.5°C) and 90°F (32°C)

24 hour Emergency "CHEM-TEL" - 800.255.3924

For Technical Information call 800.342.3755

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of this product are beyond our control. Neither ICP Construction, Inc., nor its agents shall be responsible for the use or results of use of this product or any injury, loss or damage, direct or consequential. We recommend that the prospective user determine the suitability of this product for each specific project and for the health and safety of personnel working in the area.

Fiberset PM, the Fiberset PM Logo and other marks in this literature are trademarks of ICP Construction, Inc.

150 Dascomb Rd

•

Andover, MA 01810

•

www.fiberlock.com

•

800.342.3755